

Interpon D36 Satin (70)

Product Description: **Interpon D36 Satin (70)** is a range of powder coatings intended for use on architectural aluminium and galvanised steel.

Available in a wide stock range **Interpon D36 Satin (70)** has been specifically formulated using the **Perform System**, Akzo Nobel's TGIC-free technology. As part of the **Interpon D** series of architectural powders, **Interpon D36 Satin (70)** gives excellent exterior durability and colour retention and conforms with the requirements of all the major European architectural finishing standards.

All **Interpon D36 Satin (70)** powders are lead-free and meet the requirements of GSB, Qualicoat Class 1 and EN 12206 (formerly BS6496), BS6497:1984.

Powder Properties:	Chemical type	Polyester
	Gloss (60°) ISO2813	70±5
	Particle size	Suitable for corona application
	Density	1.2-1.7 depending on colour
	Storage	Dry cool conditions below 30°C peak temperature
	Shelf life	24 months
	Sales Code	S-series
	Stoving schedule (object temperature)	10-20 minutes at 180°C 9-18 minutes at 190°C 8-16 minutes at 200°C

Test Conditions: The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

	Substrate	Aluminium (0.5-0.8mm Al Mg1)	
	Pretreatment	Chromate	
	Film Thickness	60 microns	
	Stoving	8 minutes at 200°C (object temperature)	
	Mechanical Tests:	Adhesion	ISO2409
Erichsen Cupping		ISO1520	Pass >7mm
Hardness		ISO2815	Minimum 80
Impact		ASTM D2794	Pass 2.5 joules and reverse direct or 20 inch pounds
Flexibility		ISO1519	Pass 5mm
Corrosion Tests:	Salt Spray	ISO7253	Pass at 1000 hours - no corrosion area more than 2mm from scribe
	Acetic Acid Salt Spray	ISO9227	Pass at 1000 hours - <16mm ² corrosion/10cm
	Constant Humidity	ISO6270	Pass at 1000 hours - no Blistering, creep < 1mm
	Sulphur Dioxide	ISO3231	Pass 30 cycles - no blistering, creep <1mm from scribe
	Permeability	Pressure Cooker Qualicoat B1(o)	Pass - no defects after 1 hour (2 hours boiling water)
	Chemical Resistance		Generally good resistance to dilute acids, alkalis and oils at normal temperatures
	Mortar Resistance	ASTM C207	No effect after 24 hours

Interpon D36 Satin (70)

Weathering Tests:	Exterior Durability	ISO2810 (Florida 12 months 5° South)	≥50%Gloss retention. Colour retention in accordance with GSB or Qualicoat. Chalking - none in excess of minimum in ASTM D659:1980
	Accelerated Weathering Test	Suntest Original- Hanau-Quartzlampen ISO11341	≥50% Gloss retention after 1000 hours
		QUV B313	≥50% Gloss retention after 300 hours
	Light Fastness	DIN 54004	Minimum 7

Pretreatment: For maximum protection it is essential to pretreat architectural components prior to the application of **Interpon D36 Satin (70)**. Aluminium components should receive a full multi-stage chromate conversion coating, suitable chrome-free pretreatment or suitable pre-anodising to clean and condition the substrate. Detailed advice should be sought from the pretreatment supplier.

Galvanised steel requires surface preparation by either multi-stage pretreatment using either zinc phosphate or chromate conversion or controlled sweep blasting. Depending on the type of galvanising, degassing or use of anti-bubbling additives may be required - follow the procedural advice of the pretreatment supplier.

Interpon D36 Satin (70) products may also be used on cast or mild steel. For outdoor use **Interpon PZ** anti-corrosive primer over a correctly prepared substrate is recommended.

Application: **Interpon D36 Satin (70) Gloss** can be applied by manual or automatic electrostatic spray or tribo charging equipment. For solid shades unused powder can be reclaimed using suitable equipment and recycled through the coating system. Detailed information and specific advice for special finishes is available upon request. Certain colours should be applied at higher film thickness to ensure coverage.

Post Application: For specific advice on the suitability of post coating processes such as bending or the use of sealants, adhesives, thermal break, cleaning etc. please consult Akzo Nobel.

Safety Precautions: Please consult the Material Safety Datasheet (MSDS) PC111

Disclaimer: The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.